

Polyurethane Topcoat – Type 1 & 2, Class H
TEST REPORT- PRODUCT CODE AS 1005 SERIES GLOSSY

CHEMICAL RESISTANCE					
ASTM D2792, D1308					
TEST DURATION -24 HRS					
CHEMICAL	CONCENTRATION				
	100%	50%	25%	10%	1%
Sulphuric Acid H2SO4	Good	Excellent	Excellent	Excellent	Excellent
Hydrochloric Acid HCL	Good	Excellent	Excellent	Excellent	Excellent
Nitric Acid HNO3	Good	Excellent	Excellent	Excellent	Excellent
Acetic Acid CH3COOH	Excellent	Excellent	Excellent	Excellent	Excellent
Citric Acid C6H8O7	Excellent	Excellent	Excellent	Excellent	Excellent
Chromic Acid H2CrO4	Excellent	Excellent	Excellent	Excellent	Excellent
Sodium Hydroxide NaOH	Excellent	Excellent	Excellent	Excellent	Excellent
Ammonium Hydroxide NH4OH	Excellent	Excellent	Excellent	Excellent	Excellent
Aviation Fuel	Excellent	Excellent	Excellent	Excellent	Excellent
Ethanol CH3CH2OH	Excellent	Excellent	Excellent	Excellent	Excellent
Engine Oil	Excellent	Excellent	Excellent	Excellent	Excellent
Synthetic Oil	Excellent	Excellent	Excellent	Excellent	Excellent
Lubricants	Excellent	Excellent	Excellent	Excellent	Excellent
Acetone (CH3)2CO	Excellent	Excellent	Excellent	Excellent	Excellent
Enthylene Dichloride	Excellent	Excellent	Excellent	Excellent	Excellent
Toluene	Excellent	Excellent	Excellent	Excellent	Excellent
Distilled Water	Excellent	Excellent	Excellent	Excellent	Excellent

Product by **AUTOMOTIVE SOLUTIONS. India.**

CONFIDENTIAL DOUMENT

www.automotivesolutions.net.in